

Conductive Silver Ink ARMINK

Description:

Recently new printing methods were developed to manufacture flexible electronics. Between these methods, using conductive inks has a low material waste, simple manufacturing process, low prices, large area, high precision, and many other advantages. Therefore, metal nanoparticles based conducting inks for direct patterning on flexible substrates represent the most promising manufacturing way. Ag nanoparticles for its low resistivity and stable property has been considered as the most appropriate conductive ink.

Characterization		
CAS	1003582-37-3	
Stock No.	ARMINK-S1	ARMINK-S2
Ag content (%w/v)	7-10	40
Particle size (nm)	20-60	20-60
Ink vehicle	Hydrocarbon	Water
Color	Olive	Olive
Curing temperature	RT	RT
Curing time (min)	5-15	10-20
Substrate	Glass and polymers	Paper
Viscosity	Thin liquid	Thin liquid
Sheet resistance (Ω/\square)	<0.1	<0.1
Adhesion (tape cross hatch)	No Transfer	No Transfer




Image of nano silver ink
(ARMINK)

Note: product specifications are subject to amendment and may change over time.

Drying condition:

Dry in ambient condition. No heating or blowing is needed.

Storage and Shelf life:

Keep it in cool dry place.

Avoid direct sunlight.

Do not freeze.

Do not leave it open for long time.


Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (25°C).

Shelf life of material in unopened containers is six months from date of shipment.



Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Tinning is not recommended.






Conductive Silver Ink ARMINK




(a) SEM and (b) TEM images of silver nanoparticles used in ARMINK




XRD pattern of silver nanoparticles used in ARMINK

ARMINK

Armina
Engineering Co.



Conductive Silver Ink ARMINK




SEM image of cross section of
ARMINK-S1 after drying in air



Images of printed circuit board with ARMINK-S2

ARMINK

Armina
Engineering Co.



Conductive Silver Ink ARMINK



Printability of ARMINK-S1 with 3D
printer (800 μm nozzle)

Safety:

Always use protective gloves and safety glasses.
Wash with soap and water after exposure.
Contains flammable solvents.
Avoid contact with skin and breathing of vapors.

www.armina-eng.com
Sales@armina-eng.com



Address: Floor 1, No 18.1, Danesh 1 St,
Pardis Technology Park, Tehran, Iran
Postal Code: 16541 20708
Telefax: +98 21 7625 1689



(+98) 933 759 6565