

Gold Nanoparticles AUP311

Description and Applications:

Gold nanoparticles have attracted great interests in the fields of biological and medical applications such as diagnosis of heart diseases, cancers, and infectious agents. Because of the unique surface plasmon resonance property, the surface of gold nanoparticles can be used for selective oxidation or reduce a reaction in certain cases and also can strongly absorb light (as the result of the SPR) which can efficiently be converted to heat. This makes it a useful tool for photothermal therapy of cancers or other diseases. The large surface area-to-volume ratio of gold nanoparticles enables their surface to be coated with hundreds of molecules, including therapeutics that can be used for drug delivery purposes. Also, gold has good electrical and thermal conductivity. Gold's capability to resist corrosion as well as its high electrical conductivity make it useful for forming contacts in electronic devices.

Characterization	
CAS	7440-57-5
Stock No.	AUP311
Molecular formula	Au
Molecular weight (g/mol)	196.97
Form	Water base colloid
Color	Red- Puce
Concentration	0.1 mg/mL
Functional group	Citrate
pH	6.1
Morphology	Spherical
Crystal structure	FCC
Size range (nm)	20-25
Total impurity (%)	N/A




Image of gold Nanocolloid
(AUP311)



Note: product specifications are subject to amendment and may change over time.

Safety:


Always use protective gloves and safety glasses.
Wash with soap and water after exposure.
Refer to MSDS prior to handling this material.




Gold Nanoparticles AUP311




TEM images of AUP311




XRD pattern of AUP311




Gold Nanoparticles AUP311




Size distribution by intensity of AUP311 (DLS)




Size distribution by volume of AUP311 (DLS)




Size distribution by number of AUP311 (DLS)



Gold Nanoparticles AUP311



Zeta potential distribution of AUP311 (DLS)



UV- Visible Absorption spectra of AUP311


Storage:

Store at 4-18°C.
Do not freeze.
Avoid direct sunlight.
To disperse sedimented nanoparticles sonication could be used.


Shelf life:

When stored as specified the product is stable for at least 6 month.





Gold Nanoparticles AUP311



شماره: ۳۱۲-۲۶۰۶۳
تاریخ: ۱۴۰۲/۰۸/۳۰
پیوست: ندارد

بسمه تعالی



جناب آقای دکتر ابراهیم اکبرزاده

مدیر عامل محترم شرکت مهندسی پایدار ابتکار آرمینا

با سلام و احترام، به اطلاع می‌رساند، با توجه به بررسی انجام شده، محصول "کلونید نانوذرات طلا" با ضوابط فنی گروه ارزیابی و نظارت ستاد نانو مطابقت دارد. لذا به این محصول با کد ۰۲۷۱۹۳ از تاریخ ۰۲/۰۸/۲۹ به مدت دو سال "تأیید نانومقیاس" اعطا می‌شود.

علی طهاری
مدیر عامل



تهران - خیابان ستارخان - خیابان زنگنه شمالی - کوی سیادت - پلاک ۶۵
تلفن: ۶۳۱۰۴ فکس: ۶۳۱۰۴۴۱۰ کد پستی: ۱۴۵۶۹۱۴۴۷۷
No.65, North Zanjani St., Satarkhan Ave., Tehran, Iran
www.tmsc.ir info@tmsc.ir Tel: +98 21 63104

www.nanoproduct.ir
www.htbs.ir
www.tesc.ir
www.patentoffice.ir

ارزیابی محصولات
توسعه خدمات تجاری سازی
کریستور صادرات
کانون پتنت ایران

